Subpart I-Requirements for Corrosion Control

192.451 Scope.

This subpart prescribes minimum requirements for the protection of metallic pipelines from external, internal, and atmospheric corrosion.

192.453 General.

Each operator shall establish procedures to implement the requirements of this subpart. These procedures, including those for the design, installation, operation and maintenance of cathodic protection systems, must be carried out by, or under the direction of, a person qualified by experience and training in pipeline corrosion control methods.

192.455 External corrosion control: buried or submerged pipelines installed after July 31, 1971.

(a) Except as provided in paragraphs (b) and (c) of this section, each buried or submerged pipeline installed after July 31, 1971 must be protected against external corrosion, including the following:

(1) It must have an external protective coating meeting the requirements of 192.46.

(2) It must have a cathodic protection system designed to protect the pipeline in its entirety in accordance with this subpart, installed and placed in operation within one year after completion of construction.

(b) An operator need not comply with paragraph (a) of this section, if the operator can demonstrate by tests, investigation, or experience in the area of application, including, as a minimum, soil resistivity measurements and tests for corrosion accelerating bacteria, that a corrosive environment does not exist. However, within 6 months after an installation made pursuant to the preceding sentence, the operator shall conduct tests, including pipe-to-soil potential measurements with respect to either a continuous reference electrode, or an electrode using close spacing, not to exceed 20 feet, and soil resistivity measurements at potential profile peak locations, to adequately evaluate the potential profile along the entire pipeline. If the tests made indicate that a corrosive condition exists, the pipeline must be cathodically protected in accordance with paragraph (a) (2) of this section.

(c) An operator need not comply with paragraph (a) of this section, if the operator can demonstrate by tests, investigation, or experience that—

(1) For a copper pipeline, a corrosive environment does not exist; or

(2) For a temporary pipeline with an operating period of service not to exceed 5 years beyond installation, corrosion during the 5-year period of service of the pipeline will not be detrimental to public safety.

(d) Notwithstanding the provisions of paragraph (b) or (c) of this section, if a pipeline is externally coated, it must be cathodically protected in accordance with paragraph (a) (2) of this section.

Register, June, 1974, No. 222

(e) Aluminum may not be installed in a buried or submerged pipeline if that aluminum is exposed to an environment with a natural pH in excess of 8, unless tests or experience indicate its suitability in the particular environment involved.

192.457 External corrosion control: buried or submerged pipelines installed before August 1, 1971.

(a) Except for buried piping at compressor, regulator, and measuring stations, each buried or submerged transmission line installed before August 1, 1971, that has an effective external coating must, not later than August 1, 1974, be cathodically protected along the entire area that is effectively coated, in accordance with this subpart. For the purposes of this subpart, a pipeline does not have an effective external coating if its cathodic protection current requirements are substantially the same as if it were bare. The operator shall make tests to determine the cathodic protection current requirements.

(b) Except for cast iron or ductile iron, each of the following buried or submerged pipelines installed before August 1, 1971, must, not later than August 1, 1976, be cathodically protected in accordance with this subpart in areas in which active corrosion is found:

(1) Bare or ineffectively coated transmission lines.

(2) Bare or coated pipes at compressor, regulator, and measuring stations.

(3) Bare or coated distribution lines. The operator shall determine the areas of active corrosion by electrical survey, or where electrical survey is impractical, by the study of corrosion and leak history records, by leak detection survey, or by other means.

(c) For the purpose of this subpart, active corrosion means continuing corrosion which, unless controlled, could result in a condition that is detrimental to public safety.

PSC 192.457 (d) Notwithstanding the provisions of 192.457 (b) (regarding active corrosion), effectively coated steel distribution pipelines, except for those portions including services and short sections that because of their nature and installation make cathodic protection impractical and uneconomical, must, not later than August 1, 1975, be cathodically protected along the entire area that is effectively coated in accordance with this subpart.

192.459 External corrosion control: examination of buried pipeline when exposed.

Whenever an operator has knowledge that any portion of a buried pipeline is exposed, the exposed portion must be examined for evidence of external corrosion if the pipe is bare, or if the coating is deteriorated. If external corrosion is found, remedial action must be taken to the extent required by 192.483 and the applicable paragraphs of 192.485, 192.487, or 192.489.

192.461 External corrosion control: protective coating.

(a) Each external protective coating, whether conductive or insulating, applied for the purpose of external corrosion control must—

(1) Be applied on a properly prepared surface;

(2) Have sufficient adhesion to the metal surface to effectively resist underfilm migration of moisture;

(3) Be sufficiently ductile to resist cracking;

Register, June, 1974, No. 222

302

192.611 Change in class location: confirmation or revision of maximum allowable operating pressure.

If the hoop stress corresponding to the established maximum allowable operating pressure of a segment of pipeline is not commensurate with the present class location, and the segment is in satisfactory physical condition, the maximum allowable operating pressure of that segment of pipeline must be confirmed or revised as follows:

(a) If the segment involved has been previously tested in place to at least 90% of its SMYS for a period of not less than 8 hours, the maximum allowable operating pressure must be confirmed or reduced so that the corresponding hoop stress will not exceed 72% of SMYS of the pipe in Class 2 locations, 60% of SMYS in Class 3 locations, or 50% of SMYS in Class 4 locations.

(b) If the segment involved has not been previously tested in place as described in paragraph (a) of this section, the maximum allowable operating pressure must be reduced so that the corresponding hoop stress is not more than that allowed by this part for new segments of pipelines in the existing class location.

(c) If the segment of pipeline involved has not been qualified for operation under paragraph (a) or (b) of this section, it must be tested in accordance with the applicable requirements of Subpart J of this part, and its maximum allowable operating pressure must then be established so as to be equal to or less than the following:

(1) The maximum allowable operating pressure after the requalification test is 0.8 times the test pressure for Class 2 locations, 0.667 times the test pressure for Class 3 locations, and 0.555 times the test pressure for Class 4 locations.

(2) The maximum allowable operating pressure confirmed or revised in accordance with this section, may not exceed the maximum allowable operating pressure established before the confirmation or revision.

(3) The corresponding hoop stress may not exceed 72% of the SMYS of the pipe in Class 2 locations, 60% of SMYS in Class 3 locations, or 50% of the SMYS in Class 4 locations.

(d) Confirmation or revision of the maximum allowable operating pressure of a segment of pipeline in accordance with this section does not preclude the application of 192.553 and 192.555.

(e) Confirmation or revision of the maximum allowable operating pressure that is required as a result of a study under 192.609 must be completed as follows:

(1) Confirmation or revision due to changes in class location that occur before July 1, 1973, must be completed not later than December 31, 1974.

(2) Confirmation or revision due to changes in class location that occur on or after July 1, 1973, must be completed within 18 months of the change in class location.

192.613 Continuing surveillance.

(a) Each operator shall have a procedure for continuing surveillance of its facilities to determine and take appropriate action concerning changes in class location, failures, leakage history, corrosion, substantial changes in cathodic protection requirements, and other unusual operating and maintenance conditions.

(b) If a segment of pipeline is determined to be in unsatisfactory

Register, June, 1974, No. 222

condition but no immediate hazard exists, the operator shall initiate a program to recondition or phase out the segment involved, or, if the segment cannot be reconditioned or phased out, reduce the maximum allowable operating pressure in accordance with 192.619 (a) and (b).

PSC 192.613 (c) When street is paved or repaved. Whenever a road or street is paved or repaved with permanent pavement, the operator shall:

(1) Check for leaks along all mains and services in the streets and abutting property. The check shall be conducted by testing with a combustible gas indicator air samples taken from holes placed near the pipes. The utility may substitute for bar hole tests a ground surface survey with a continuous-sampling instrument capable of detecting combustible gas in air concentrations of 100 parts per million.

(2) Determine condition of pipe and joints by sample visual examination.

(3) Place clamps on, reconstruct, or repair joints if they are likely to dry out or are leaking.

(4) Replace pipe if existing pipe is corroded to such an extent that it is likely to require replacement before the street is again resurfaced.

PSC 192.613 (d) Underground pipes. Whenever underground pipes are exposed in order to repair leaks, the utility shall record on the repair order the nature of the leak and possible cause from observation.

192.615 Emergency plans.

Each operator shall-

(a) Have written emergency procedures;

(b) Acquaint appropriate operating and maintenance employees with the procedures;

(c) Establish liaison with appropriate public officials, including fire and police officials, with respect to the procedures; and

(d) Establish an educational program to enable customers and the general public to recognize and report a gas emergency to the appropriate officials.

192.617 Investigation of failures.

Each operator shall establish procedures for analyzing accidents and failures, including the selection of samples of the failed facility or equipment for laboratory examination, where appropriate, for the purpose of determining the causes of the failure and minimizing the possibility of a recurrence.

192.619 Maximum allowable operating pressure: steel or plastic pipelines.

(a) Except as provided in paragraph (c) of this section, no person may operate a segment of steel or plastic pipeline at a pressure that exceeds the lowest of the following:

(1) The design pressure of the weakest element in the segment, determined in accordance with Subparts C and D of this part.

(2) The pressure obtained by dividing the pressure to which the segment was tested after construction as follows:

(i) For plastic pipe in all locations, the test pressure is divided by a factor of 1.5.

Register, June, 1974, No. 222

316

(3) Notwithstanding the alternative minimum criteria in subparagraphs (1) and (2) of this paragraph, aluminum, if cathodically protected at voltages in excess of 1.20 volts as measured with reference to a copper-copper sulfate half cell, in accordance with section IV of this appendix, and compensated for the voltage (IR) drops other than those across the structure-electrolyte boundary, may suffer corrosion resulting from the buildup of alkali on the metal surface. A voltage in excess of 1.20 volts may not be used unless previous test results indicate no appreciable corrosion will occur in the particular environment.

(4) Since aluminum may suffer from corrosion under high pH conditions, and since application of the cathodic protection tends to increase the pH at the metal surface, careful investigation or testing must be made before applying cathodic protection to stop pitting attack on aluminum structures in environments with a natural pH in excess of 8.

C. Copper structures. A minimum negative (cathodic) polarization voltage shift of 100 millivolts. This polarization voltage shift must be determined in accordance with sections III and IV of this appendix.

D. Metals of different anodic potentials. A negative (cathodic) voltage, measured in accordance with section IV of this appendix, equal to that required for the most anodic metal in the system must be maintained. If amphoteric structures are involved that could be damaged by high alkalinity covered by subparagraphs (3) and (4) of paragraph B of this section, they must be electrically isolated with insulating flanges, or the equivalent.

II. Interpretation of voltage measurement. Voltage (IR) drops other than those across the structure-electrolyte boundary must be considered for valid interpretation of the voltage measurement in paragraph A (1) and (2) and paragraph B (1) of section I of this appendix.

III. Determination of polarization voltage shift. The polarization voltage shift must be determined by interrupting the protective current and measuring the polarization decay. When the current is initially interrupted, an immediate voltage shift occurs. The voltage reading after the immediate shift must be used as the base reading from which to measure polarization decay in paragraphs A (3), B (2), and C of section I of this appendix.

IV. Reference half cells. A. Except as provided in paragraphs B and C of this section, negative (cathodic) voltage must be measured between the structure surface and a saturated copper-copper sulfate half cell contacting the electrolyte.

B. Other standard reference half cells may be substituted for the saturated copper-copper sulfate half cell. Two commonly used reference half cells are listed below along with their voltage equivalent to -0.85 volt as referred to a saturated copper-copper sulfate half cell:

(1) Saturated KC1 calomel half cell: -0.78 volt.

(2) Silver-silver chloride half cell used in sea water: -0.80 volt. C. In addition to the standard reference half cells, an alternate metallic material or structure may be used in place of the saturated copper-copper sulfate half cell if its potential stability is assured

Register, June, 1974, No. 222

and if its voltage equivalent referred to a saturated copper-copper sulfate half cell is established.

Note: Copies of the publications referred to are available for inspection at the office of the public service commission, the secretary of state and the revisor of statutes or may be procured for personal use from the addresses listed in 192.753.

History: Cr. Register, May, 1972, No. 197, eff. 6-1-72; cr. 192.12, 192.379. appendix A-II F 4; am, 192.201 (a), 192.625 (g) (1), 192.717 (b), 192.727. Register, February, 1973, No. 206, eff. 3-1-73; am, PSC 192.457 (d), PSC 192.613 (c) (1), Register, June, 1974, No. 222, eff. 7-1-74.

Next page is numbered 337

Register, June, 1974, No. 222

334